



Technical Report No. 64.160.17.01874.01

Rev. 00

Dated 2017-05-24

Client: **FILIPPI LEGNAMI**
VIA NAZARIO SAURO, 2 BERBENNO-BERGAMO-ITALY

Test Subject: **The submitted sample was identified and described by client as:**
Poplar Plywood

Country of origin: **ITALY**

Test Requested: **1. Formaldehyde Release Test**

Test Result: **Please refer to next page(s)**


Conclusion: **1. Formaldehyde Release Test**

Report as is

Remarks: **(1) The results relate only to the items tested.**
(2) Samples are tested as received.

This technical report may only be quoted in full. Any use for advertising purposes must be granted in writing. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production.

1 Description of the test subject

Sample No.	Color and description	Photograph
001	Light-brown plywood with brown surface	

2 Order

2.1 Date of Purchase Order

2017-05-18

2.2 Receipt of Test Sample, Location

2017-05-18, Guangzhou

2.3 Date of Testing

2017-05-18 to 2017-05-24

2.4 Location of Testing

The test was performed in TÜV SÜD Certification and Testing (China) Co., Ltd. Shenzhen Branch chemical lab and the test results were reviewed at TÜV SÜD Certification and Testing (China) Co., Ltd. Guangzhou Branch.



3 Test Results

3.1 Formaldehyde Release Test

For reference: Formaldehyde release class E1: $\leq 3.5 \text{ mg/m}^2\text{h}$

Formaldehyde release class E2: $\leq 8 \text{ mg/m}^2\text{h}$

Test Method: Detection by EN standard.

Test items	Unit	Test Method	Result	MDL
			Sample 001	
Formaldehyde Release	mg/m ² h	EN ISO 12460-3:2015	2.6	0.1

Note: 1. MDL= Method Detection Limit

2. mg/m²h means milligram per square metres per hour



TÜV SÜD Certification and Testing (China) Co., Ltd. Guangzhou Branch
TÜV SÜD Group



Engineer: 
Lily Feng

Technical Report checked: 

Kevin Zhang

- END OF TEST REPORT -